



Black Diamond Pavement Sealer Concentrate

DESCRIPTION:

GemSeal® Black Diamond Concentrate is a premium petroleum-based emulsion pavement sealer, designed for application to pavement surfaces. GemSeal® Black Diamond weatherproofs asphalt surfaces, seals against penetration by water, oil, and blocks the destructive drying action of the sun by forming a tough protective membrane with a deep black color. GemSeal® Black Diamond extends the service life and enhances the appearance to provide a cost effective preventive maintenance coating of asphalt surfaces.

FEATURES:

- Formulated specifically to protect all asphalt surfaces including commercial and residential parking areas and driveways.
- Alternative to both refined tar and asphalt base sealers.
- Weatherproofs and seals porous asphalt surfaces, preventing damaging effects of water penetration.
- Protects pavements from oxidation by forming a tough protective skin with a deep black color.
- Exhibits outstanding wear resistance.
- Manufactured in a regulated continuous process for consistent emulsion particle size and distribution.
- Resists gasoline and oil penetration.

DESCRIPTION:

Property	Max.	Min.
Water (%)	53	48
Non-Volatile (%)	52	47
Ash (%)	39	35
Sp. Gr. @ 77°	1.29	1.19

SPECIFICATIONS:

Meets the following standards listed below:

- | | |
|------------|-------------|
| ASTM D 140 | ASTM D 529 |
| ASTM D 466 | ASTM D 2939 |

GemSeal Black Diamond does not contain refined coal tar but does meet the performance standards listed in:

- | | |
|-------------|-----------------------------|
| ASTM D 5727 | ASTM D3423 |
| ASTM D490 | FAA P-625; P-627; and P-630 |

MIX DESIGNS:

GemSeal® Black Diamond is a concentrate designed to be thoroughly blended with potable water, mineral aggregate and additives in proportions according to the mix designs described in the table below.

MIX DESIGNS (cont.)

GemSeal® Black Diamond	Water	Graded Aggregate ¹	Latex ² Polymer
(GAL)	(GAL)	(LB)	(GAL)
100	30-35	200-300 ⁴	1-2
100	30-40	200-400 ⁴	2-3

*Note: sub-tropical regions may require 10% more water

1. Mineral Aggregate - Introduction of clean, washed, well graded, medium to fine silica or boiler slag mineral aggregate is recommended to provide added traction to the cured coating, in addition to filling hairline voids in the asphalt. 40-70 mesh aggregate size is recommended.
2. Latex Polymer - Field proven in mix designs for best performance with GemSeal® Black Diamond should include the use of GemSeal® Boost Pro, GemSeal® Rapid Set or GemSeal® GuardFlex.
3. Mix designs containing in excess of 40 gal. water per 100 gal. Black Diamond are not recommended, as curing and wear can be affected.
4. USE ONLY GEMSEAL polymer fortifiers specifically designed for Black Diamond. DO NOT USE other additives. Other additives are not chemically compatible with GemSeal® Black Diamond and will degrade the emulsion.

APPLICATION RATE:

0.10-0.15 Gal/Sq.Yd. (per coat)

Pavement Use	Application Rate gal/ sq.yd.	Coats
Low Traffic	.10 - .15	2
Moderate Traffic	.12 - .15	2
High Traffic	.12 - .15	3

Fueling or truck maintenance areas may require an additional lightly sanded coat.



Black Diamond Pavement Sealer Concentrate

SURFACE PREPARATION:

Pavement surface must be sound, free of debris, vegetation, dust, oils, grease and detergent residues. Accumulations of petroleum deposits, tree sap and dirt should be scraped clean and treated with GemSeal® Tar Prime. Narrow surface cracks should be filled with GemSeal® Pourable Crack Filler, GemSeal® Trowelable Crack Filler, or a suitable hot-applied joint sealant. Wide cracks, severely distressed, alligatored or deteriorated pavement surfaces should be repaired. New asphalt paving or repair patches should be allowed to cure a minimum of 60 days at temperatures of 60°F or above before seal coating begins. New Asphalt paving or repair patches should not show oil rings when 1 gallon of clean water is poured onto the surface.

APPLICATION:

GemSeal® Black Diamond can be applied using spray or mechanical squeegee equipment capable of controlled, uniform distribution of material conforming to mix designs and application rates specified. Material can also be applied with brush or rubber squeegee applicator designed for these products.

GemSeal® Black Diamond should be applied only when pavement and ambient temperatures are continuously above 50°F for at least 24 hours following application and no rain is forecast for that period. Allow adequate drying time between successive coats.

Cooler temperatures (below 70°F) and/or damp or overcast conditions will lengthen curing times.

Notes: Sealcoating is not recommended for enclosed or permanently shaded parking areas such as underground parking garages.

PACKAGING:

Available in 55-gallon drums and tank truck up to 4,500 gallons.

SERVICE:

Timely service is available within 300 mile radius of our manufacturing facilities.

ATTENTION:

GemSeal® Black Diamond should be protected from freezing.

CAUTION:

WARNING: This product contains chemicals known to the State of California to cause cancer, birth defects or other reproductive harm.
Two percent of the mixture consists of ingredient(s) of unknown acute toxicity

MANUFACTURING & CUSTOMER SERVICE:

Call (866) 264-8273 to find the nearest GemSeal location to purchase Black Diamond Pavement Sealer Concentrate.

GemSeal is a registered trademark of Bonsal American, an Oldcastle company



Bonsal American, Inc.
Corporate Headquarters:
8201 Arrowridge Blvd. Charlotte, NC 28273

LIMITED 1 YEAR PRODUCT WARRANTY FROM DATE OF MANUFACTURE: Bonsal American warrants that this product and the materials used therein meet or exceed the applicable standards listed and enforced at the time of manufacture. Bonsal American will replace any product or part which proves defective due to quality of ingredients used or due to the manufacturing process itself. This Warranty shall apply only if the product is used in strict accordance with applicable specifications and instructions provided by Bonsal American for its use, and Bonsal American shall not be liable otherwise. Replacement of any defective product, or, at Bonsal American option, refund of the purchase of any defective product shall be the buyer's sole remedy under this Warranty, and Bonsal American shall in no event be liable for any damages in excess of the purchase price of the defective product. **BONSAL AMERICAN SHALL IN NO EVENT BE LIABLE FOR ANY CONSEQUENTIAL, INCIDENTAL, OR SPECIAL DAMAGES.**

This Warranty constitutes the sole warranty given by Bonsal American in connection with this product, and Bonsal American has authorized no person to make or give any other warranties or representation, oral or written on its behalf. **IN PARTICULAR, THERE ARE NO IMPLIED WARRANTIES, INCLUDING WITHOUT EXCEPTION WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** No modification of this Warranty in favor of any buyer shall be valid unless given in writing and signed by an officer of Bonsal American.